

DERWENT-ACC-NO: 1985-128628

DERWENT-WEEK: 198522

COPYRIGHT 1999 DERWENT INFORMATION LTD

TITLE: Prodn. of activated carbon adsorbent
from brown coal -
addn. of heavy metal with increased meso-pore content by
salt before thermal activation

INVENTOR: HOPPE, H; HUSCHENBE, R ; RIEDEL, D ; SCHNEGULA, E
; WINKLER, F

PATENT-ASSIGNEE: TECH HOCH SCHORLEMM[TEHON]

PRIORITY-DATA: 1983DD-0255174 (September 28, 1983)

PATENT-FAMILY:

PUB-NO	PAGES	PUB-DATE	MAIN-IPC
DD 218075 A		January 30, 1985	N/A
003	N/A		

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO
DD 218075A	N/A	
1983DD-0255174	September 28, 1983	

INT-CL (IPC): C01B031/10

ABSTRACTED-PUB-NO: DD 218075A

BASIC-ABSTRACT:

Prodn. of activated carbon from brown coal high-temp. coke
comprises: (i)
treatment of the coke with a 3-15 (pref. 5-10) wt.% soln.
of the salt of a
heavy metal (pref. Fe(II), Fe(III), Ni or Co); and (ii)
activation by heating
to 850-1000 deg.C e.g. in steam. The aq. soln. of the
heavy metal salt may be

sprayed onto the coke, and the mixt. intensively mixed before being activated.

USE/ADVANTAGE - The prod. can be used for purificn. of water and air. As a result of step (i), the prod. contains, in addn. to a well-formed micropore system, a pronounced mesopore system by which larger mols. are transported more rapidly to the sorption centres. A pronounced meso- and macropore system is necessary in special carbons for purificn. of dye-contg. water or removal of organic impurities in the foodstuffs industry.

CHOSEN-DRAWING: Dwg.0/0

TITLE-TERMS: PRODUCE ACTIVATE CARBON ADSORB BROWN COAL
INCREASE MESO PORE
CONTENT ADD HEAVY METAL SALT THERMAL ACTIVATE

DERWENT-CLASS: E36 H09 J01

CPI-CODES: E31-N03; J01-D01; J01-E02B; J01-E03;

CHEMICAL-CODES:

Chemical Indexing M3 *01*

Fragmentation Code

C106 C810 M411 M720 M903 M910 N515 Q231 Q418 Q508
R032

UNLINKED-DERWENT-REGISTRY-NUMBERS: 1669P; 1939S

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C1985-055975